## AMENDMENTS TO THE CLAIMS:

The following listing of claims will replace all prior versions and listings of claims in the application.

Claim 1 (currently amended) A process for the production of a cellular composite comprising consisting essentially of:

- (A) preparing a mixture <u>consisting essentially</u> of (1) a polyisocyanate and (2) water;
- (B) adding the mixture formed in (A) to (3) Inorganic hollow microspheres under low shear mixing;
- (C) completely filling a mold with the mixture formed in (B); and
- (D) heating the filled mold at a temperature of from 100 to 280°C; thereby reacting the polylsocyanate and water to form a polyurea which binds the hollow microspheres, thus forming a cellular composite.

Claim 2 (canceled)

Claim 3 (canceled)

Claim 4 (original) The process of Claim 1, wherein (D) said heating is at a temperature of from 125 to 150°C.

Claim 5 (original) The process of Claim 1, wherein (B)(3) said inorganic hollow microspheres are selected from the group consisting of glass, silicates, borosilicates, ceramic, fly-ash and mixtures thereof.

Claim 6 (original) The process of Claim 1, wherein (A)(1) said polylsocyanate is characterized by an NCO group content of from 25 to 35% by weight, and a functionality of from 2.0 to 3.5, a viscosity of less than about 500

MO-6806

mPa s at 25°C, and is selected from the group consisting of aromatic polyisocyanates, and adducts and mixtures thereof.

Claim 7 (original) The process of Claim 1, wherein (A)(2) said water is present in an amount such that there is an excess of from 2 to 5 times the stoichiometric quantity required based on the NCO group content of (A)(1) said polylsocyanate.

Claim 8 (original) The process of Claim 1, wherein (D) said heating continues from 0.5 to 60 minutes.

Claim 9 (original) A cellular composite produced by the process of Claim 1.